

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-208313

(43)Date of publication of application : 12.08.1997

---

(51)Int.Cl.

C04B 35/52  
C01B 31/08  
H01G 9/058

---

(21)Application number : 08-014490

(71)Applicant : KYOCERA CORP

(22)Date of filing : 30.01.1996

(72)Inventor : TOSHIRO NAOTOMO  
HARA MASATAKE

---

(54) SOLID ACTIVATED CARBON AND PRODUCTION OF THE SAME AND ELECTRIC  
DOUBLE LAYER CAPACITOR USING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a solid activated carbon having high strength, preventing breakage is use when used as an electrode of an electric double layer capacitor, by adding a specific component to activated carbon powder and/or activated carbon fiber.

SOLUTION: This solid activated carbon comprises activated carbon powder and/or activated carbon fiber, a carbide obtained by heat treating the binder component such as a thermosetting resin, etc., and a silicone or silicone compound obtained by heat treating a silane coupling agent. The activated carbon is obtained by mixing its powder and/or fiber and the binder component such as the thermosetting resin, etc., and silane coupling agent, molding the obtained mixture and heat treating under non-oxidizing atmosphere. The addition amount of the silane coupling agent is preferably in a range of 1-150 pts.wt. per 100 pts.wt. of activated carbon powder and/or fiber. The mixing ratio of a solid component consisting of activated carbon powder and/or fiber and binder is set to be 50-95wt.% solid component and 5-50wt.% binder.